

# DANOFLOOR PRIMER PU



## Moisture Cured Clear Polyurethane Primer

### DESCRIPTION

**DANOFLOOR PRIMER PU** is specially formulated penetrating low viscous moisture cured polyurethane clear primer for use on cementitious and masonry substrates.

### USES

**DANOFLOOR PRIMER PU** is recommended for use with TIKIDAN polyurethane range of floor coatings and toppings, PUF, and other polyurethane based systems as primer to enhance the adhesion of the treatment with the substrates.

### ADVANTAGES

- Low viscous
- High penetrating power and surface pore sealing efficiency
- Good adhesion with various substrates and polyurethane top coats, PUF, etc.
- Binds left over dust particles during substrate preparation increasing bond of subsequent coats

### APPLICATION

Clean the concrete surface thoroughly free of dust. The prepared concrete surface should be free from surface condensation and moisture, surface porosities, cracks, honey combs etc. The temperature of the concrete substrate must be, at least, 3°C above dew point temperature.

Residual moisture content in the concrete should not be more than 4%.

**DANOFLOOR PRIMER PU** is supplied as ready to use single component product. Stir well the contents of pack before applying.

Apply **DANOFLOOR PRIMER PU** by brush / roller @ 8 to 9 m<sup>2</sup>/ltr./coat. Allow the primer to cure for 5 to 7 hour.

Once the applied primer is dry, the surface is ready to receive TIKIDAN PU flooring systems, PUF and other polyurethane based systems.

Once the applied prime coat of **DANOFLOOR PRIMER PU** is fully cured and is more than 24 hours old, it will not allow adhesion of subsequent top coat. In such cases, it is recommended to re-apply one coat of **DANOFLOOR PRIMER PU** or the dried prime surface should be mechanically abraded to have better mechanical key for subsequent top coating.

### APPLICATION DATA

Application	By brush / roller
Recommended Thickness	50 microns D.F.T
Theoretical Coverage	8 to 9 m <sup>2</sup> /ltr/coat @50 microns

### PROPERTIES

Properties	Values	Test Standard
Solid Content by Volume	38 to 44%	ASTM D2697
Flash Point	>20°C	ASTM D3278
Dry Time Tack Free Hard Dry	3 to 4 Hours 24 Hours	ASTM D 1640
Pull Off Adhesion On Concrete On Kota Stone	Concrete Failure 7 to 8 MPa	ASTM D4541

### SUPPLY

**DANOFLOOR PRIMER PU** is supplied in 5 and 20 litre packs. It has a shelf life of 6 months when stored under the covered shed in sealed condition.

## CLEANING

Immediately after application of **DANOFLOOR PRIMER PU**, use suitable aromatic solvent for cleaning application tools.

## STORAGE

**DANOFLOOR PRIMER PU** must be stored above 5°C. Store under the shed & protect from extremes of temperature, heat, direct sunlight, sparks and children.

## SAFETY PRECAUTIONS

As with all chemical products, care should be taken during use and storage of **DANOFLOOR PRIMER PU**.

**Disclaimer:** **TIKI TAR DANOSA** warrants that each of its products will be manufactured in accordance with the specifications in effect on the date of manufacture. While **TIKI TAR DANOSA** endeavors to ensure that information given herein is correct to the best of our knowledge, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it. We recommend that you to determine if this product meet all of your requirements perform adequate tests.

**Note:** Properties subject to change as per specific requirement. Field service where provided does not constitute supervisory responsibility. Suggestions made by **TIKIDAN** orally or in writing may be followed, either modified or rejected by the owner, engineer or contractor since they, and not **TIKIDAN**, are responsible for carrying out procedures appropriate to a specific application. **TIKIDAN** reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with the conditions and technical specifications in force at the date of order.

## TIKITAR DANOSA (INDIA) PRIVATE LIMITED

Tiki Tar Estate, Village Road, Bhandup (W), Mumbai - 400 078,  
Maharashtra, India. T: +91 22 4126 6699  
E: [info@tikidan.in](mailto:info@tikidan.in) | W: [www.tikidan.in](http://www.tikidan.in)

