

DANOKOTE EP



Solvent Free Epoxy Based Floor Coating

DESCRIPTION

DANOKOTE EP is solvent free two component epoxy based seamless floor coating system used to create easy to clean, hygienic, durable, and low maintenance flooring surface.

ADVANTAGES

- Seamless system
- High gloss and smooth finish
- Excellent adhesion to primed concrete
- Good chemical and abrasion resistance
- Does not encourage microbial growth
- Non-dusting easy to maintain system
- Slip resistant, even when wet

USES

DANOKOTE EP is preferred floor coating system for use on floors requiring good abrasion and chemical resistance coupled with easy to clean and maintain floors in various industries, which includes:

- Pharmaceutical, food and dairy industries
- Hospital clean rooms and laboratories
- Electronic assembly shops and computer rooms
- Power plants, generator rooms and pump houses
- Industrial kitchens and light duty floors
- Automobile and engineering industries
- Retail centres and departmental stores
- Aircraft hangers and other areas

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

The surfaces must be sound, clean, dry, and free from cracks, undulations, oil, grease, laitance and loose particles.

New concrete surfaces should be minimum 28 days old and should be sound with tensile strength >1.5 mPa and moisture content <4%.

SURFACE PRIMING

Apply **DANOFLOOR PRIMER EP** epoxy based primer @6 to 8 m²/Kg., on well prepared substrate covering the entire area uniformly. Allow the primer to dry. On very absorbent or porous surface, it is necessary to apply second coat of primer.

APPLICATION

DANOKOTE EP is supplied as pre-weighed two components, ready to use at site. The components of **DANOKOTE EP** shall be mixed by taking **DANOKOTE EP Pigmented Resin** component in a clean container followed by addition and gradual mixing of **DANOKOTE EP Hardener** component using slow speed heavy duty electric stirrer to achieve homogeneous and uniform coloured mix.

The prepared mix of **DANOKOTE EP** is applied by brush or roller or squeegee @0.25 Kg./m² to 0.35 Kg./m². Minimum two coats are recommended, the second coat applied perpendicular to first after first coat is dried.

Allow the applied system to cure for 24 hours before allowing foot traffic and cure for 7 days before subjecting the floor to vehicular traffic.

APPLICATION DATA

Mix Ratio PBW (Resin: Hardener)	100 : 25
Pot life at 30°C	≈ 45 Minutes
Curing Schedule Foot Traffic/ Light Load Full Traffic Load	24 to 48 Hrs 7 Days
Coverage per Pack @ 150 micron / coat	100m ²

PROPERTIES OF APPLIED PRODUCT*

Properties	Values	Test Standard
Compressive strength	>35N/mm ²	ISO 604
Flexural strength	>45 N/mm ²	ISO 178
Tensile strength	>20 N/mm ²	ISO 527
Bond strength	35 Kg/cm ² (Concrete Failure)	ASTM D4541
Abrasion Resistance (CS10, 1000 Cycles)	< 0.10gm.	ASTM D4060
Impact Resistance	>8 Joules	ASTM D2794
Dry Heat Resistance	50°C to 70°C	ASTM D2485
Scratch Resistance	No Failure @2.5Kg.	BS 3900 Part E2

*Properties tested under laboratory condition for specimens cured for 15days @30°C. Properties may vary based on actual site conditions.

CHEMICAL RESISTANCE PROPERTIES

Resistance to various chemicals at ambient temperature (25 - 35°C) (6 months immersion)			
No.	Chemical	Concentration	Observation
1.	Acetic acid	5%	Resistant
2.	Hydrochloric acid	20%	Resistant
3.	Sulphuric acid	50%	Resistant
4.	Nitric acid	10%	Resistant
5.	Phosphoric acid	30%	Resistant
6.	Salt solution	Concentrated	Resistant
7.	Sodium hydroxide	30%	Resistant
8.	Fruit juice	-	Resistant

Disclaimer: TIKI TAR DANOSA warrants that each of its products will be manufactured in accordance with the specifications in effect on the date of manufacture. While TIKI TAR DANOSA endeavors to ensure that information given herein is correct to the best of our knowledge, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it. We recommend that adequate tests be performed by you to determine if this product meet all of your requirements.

Note: Properties subject to change as per specific requirement. Field service where provided does not constitute supervisory responsibility. Suggestions made by TIKIDAN either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not TIKIDAN, are responsible for carrying out procedures appropriate to a specific application. TIKIDAN reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with the conditions and technical specifications in force at the date of order

TIKITAR DANOSA (INDIA) PRIVATE LIMITED

Tiki Tar Estate, Village Road, Bhandup (W), Mumbai - 400 078,
Maharashtra, India. T: +91 22 4126 6699
E: info@tikidan.in | W: www.tikidan.in

CLEANING

Immediately after application of **DANOKOTE EP**, use suitable aromatic solvent for cleaning application tools.

SUPPLY

DANOKOTE EP is supplied in 25 Kg. pack. It has a shelf life of 12 months when stored under the covered shed in sealed condition.

Packing: 25 Kg.

Pigmented Resin	Hardener
20 Kg.	5 Kg.

STORAGE

DANOKOTE EP must be stored above 5°C. Store under the shed & protect from extremes of temperature, heat, direct sunlight and children.

SAFETY PRECAUTIONS

As with all chemical products, care should be taken during use and storage of **DANOKOTE EP**.