

Solvent Free Polyurethane Concrete Flooring System

TIKICRETE MF is four component polyurethane concrete flooring system. It is a solvent free, seamless flooring system for use in medium to heavy duty traffic areas. The system provides high impact and abrasion resistance flooring system coupled with resistance to wide spectrum of chemicals.

ADVANTAGES

- Seamless and microbiologically inert
- High abrasion, chemical and impact resistance
- Quick return to traffic (foot traffic < 10hrs. vehicular traffic < 24hrs.)
- Non-dusting easy to maintain system
- Suitable for application on 7 day old concrete surface / 2 day old polymer screeds

USES

TIKICRETE MF is preferred flooring system for use on floors requiring high abrasion, chemical and impact resistance coupled with easy to clean and maintain floors in various industries, which includes:

- Pharmaceutical and food industries
- Dairy and beverage processing units
- Super markets and warehouses
- Chemicals and process industries
- Power plants and electronic assembly units
- Hospitals and industrial kitchen areas
- Automobile and engineering industries

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

The surfaces must be sound, clean, dry, and free from cracks, undulations, oil, grease, laitance and loose particles.

New concrete surfaces should be minimum 7 days old and should be sound with tensile strength >1.5 mPa.

All joints in the substrate should be maintained or provided wherever required, in locations with anticipated movements – viz., construction joints, areas adjacent to machine bases, columns, metal channels, while laying **TIKICRETE MF** flooring system.

Locking chase or termination grooves shall be cut in square, at least twice the thickness of **TIKICRETE MF**, on to the concrete substrate within 75mm of all free edges, perimeter walls, joints, column bases, door thresholds, and drainage channels etc., the chase / groove filled with **TIKICRETE MF** Scratch Coat.

All movement joints in the concrete substrate should be reflected through the **TIKICRETE MF** floor and sealed with a **TIKISEAL PU40** polyurethane sealant.

APPLICATION DATA

Mix Ratio PBW Scratch Coat (Resin : Hardener : Filler)	15 : 15 : 70
Body Coat (Resin: Hardener: Filler: Colouring Liquid/paste)	15 : 15 : 70 : 1.25
Pot life at 25°C	5 to 10 Min
Curing Schedule Foot Traffic Full Traffic	8 to 10 Hrs 24 Hrs
Coverage per Pack Scratch Coat @ 1mm Thickness Body Coat @ 3mm Thickness Total System (1mm Scratch Coat+3mm Body Coat)	9 to 10 m ² 3 to 3.5m ² 2 to 2.5 m ²

APPLICATION

TIKICRETE MF shall be installed only by trained and approved specialist contractors

SCRATCH COAT

Mixing: Take **TIKICRETE MF Resin** component in a clean container followed by addition and gradual mixing of **TIKICRETE MF Hardener** component under continuous stirring. To the mixture, add **TIKICRETE MF Filler** component under continuous stirring until homogeneous mix is obtained.

Scratch Coat: Prior to application of **TIKICRETE MF** flooring system, the prepared mix of **TIKICRETE MF** Scratch coat is applied by spreading the mix @ 1mm thickness using toothed trowel to cover imperfections in the substrate. Allow the scratch coat to dry.

If the applied scratch coat is left for more than 48 hours, abrade the scratch coat surface mechanically to produce a suitable surface for the application of body coat (topcoat) **TIKICRETE MF**.

BODY COAT (TOP COAT)

Mixing: **TIKICRETE MF** is supplied as pre-weighed four components, ready to use at site. The components of **TIKICRETE MF** shall be mixed by taking **TIKICRETE MF Resin** component in a clean container followed by addition and gradual mixing of **TIKICRETE MF Colouring** component using slow speed heavy-duty electric stirrer to achieve homogeneous and uniform coloured mix. To the coloured mix is then added to **TIKICRETE MF Hardener** component under continuous stirring followed by gradual addition of **TIKICRETE MF Filler** component under continuous stirring until homogeneous mix is obtained.

Body Coat (Top Coat): The prepared mix of **TIKICRETE MF** is spread using toothed trowel and immediately rolled using spike roller to remove air entrapment and avoid pinhole formation, while maintaining minimum thickness of 3mm.

Allow the applied system to cure for 24 hours before allowing vehicular traffic.

Depending on the requirement, **TIKICRETE MF** Body coat shall be applied at 3 to 6mm thickness. Ensure that the entire prepared mix of **TIKICRETE MF** is used within its pot life (5 to 10 minutes).

PROPERTIES OF APPLIED PRODUCT*

Properties	Values	Test Standard
Compressive Strength	>50 mPa	ISO 604
Flexural Strength	>18 mPa	ISO 178
Tensile Strength	>7 mPa	ISO 527
Impact Strength	>8 KJ/m ²	ISO 179
Bond Strength	35Kg/cm ² (Concrete Failure)	ASTM D4541
Abrasion Resistance	<0.150 gm	ASTM D4060, CS-17 Wheel
Impact Resistance	>20 Joules	ASTM D2794
Dry Heat Resistance	80°C to 100°C	ASTM D2485
Shore D Hardness	> 80	ISO 868

*Properties tested under laboratory condition for specimens cured for 15days @30°C. Properties may vary based on actual site conditions.

CLEANING

Immediately after application of **TIKICRETE MF**, use water for cleaning application tools.

CHEMICAL RESISTANCE PROPERTIES

No.	Chemical	Concentration	Observation
1.	Acetic acid	30%	Resistant
2.	Hydrochloric acid	30%	Resistant
3.	Sulphuric acid	50%	Resistant
4.	Nitric acid	10%	Resistant
5.	Phosphoric acid	30%	Resistant
6.	Salt solution	Concentrated	Resistant
7.	Sodium hydroxide	30%	Resistant
8.	Water	-	Resistant
9.	Lactic	10%	Resistant
10.	Citric acid	10%	Resistant
11.	Petrol	-	Resistant
12.	Oil	-	Resistant
13.	Fruit juice	-	Resistant
14.	Skydrol	-	Resistant

SUPPLY

TIKICRETE MF is supplied in 20.25 Kg, pack. It has a shelf life of 12 months when stored under the covered shed in sealed condition.

Packing:20.25kg

Product	Resin	Hardener	Colouring Paste	Filler
Pack Size	3 Kg.	3 Kg.	0.25 Kg.	14 Kg.

STORAGE

TIKICRETE MF must be stored above 5°C. Store under the shed & protect from extremes of temperature, heat, direct sunlight and children.

SAFETY PRECAUTIONS

As with all chemical products, care should be taken during use and storage of **TIKICRETE MF**.

Disclaimer: **TIKI TAR DANOSA** warrants that each of its products will be manufactured in accordance with the specifications in effect on the date of manufacture. While **TIKI TAR DANOSA** endeavors to ensure that information given herein is correct to the best of our knowledge, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it. We recommend that adequate tests be performed by you to determine if this product meet all of your requirements.

Note: Properties subject to change as per specific requirement. Field service where provided does not constitute supervisory responsibility. Suggestions made by **TIKIDAN** either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not **TIKIDAN**, are responsible for carrying out procedures appropriate to a specific application. **TIKIDAN** reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with the conditions and technical specifications in force at the date of order.

TIKITAR DANOSA (INDIA) PRIVATE LIMITED

Tiki Tar Estate, Village Road, Bhandup (W), Mumbai - 400 078,
Maharashtra, India. T: +91 22 4126 6699

E: info@tikidan.in | W: www.tikidan.in

