

# DANOFLOOR PRIMER EP



## Epoxy Based Primer

### DESCRIPTION

**DANOFLOOR PRIMER EP** is specially formulated two component epoxy primer suitable for application on various substrates for promoting adhesion of Epoxy / polyurethane floor coating and floor topping systems.

### ADVANTAGES

- Low exothermic in nature
- Extended workability and pot life
- Bonds strongly with the concrete, masonry, epoxy and polyurethane screeds, top coats and other substrates
- Non-blushing in humid and low temperature environments

### USES

**DANOFLOOR PRIMER EP** is used

- To promote the adhesion of TIKIDAN epoxy and polyurethane range of floor toppings, coatings and repair mortars with various substrates including cementitious, metals, epoxies & polyurethane.
- To seal substrate pores and bind loose particles on substrates enhancing the adhesion of subsequent coatings / toppings.
- As primer / sealer coat over the TIKIDAN epoxy and polyurethane cementitious underlays, before application of polymeric overlays.

### APPLICATION INSTRUCTIONS

#### SURFACE PREPARATION

All surfaces should be sound, clean, and dry, free from cracks, honeycombs, oil, grease, laitance and loose particles.

Newly laid cementitious systems should be at least 28 days old.

### APPLICATION

Gradually mix **DANOFLOOR PRIMER EP Resin** component and **DANOFLOOR PRIMER EP Hardener** component for 3 to 5 minutes until it becomes homogeneous. Apply mixed component immediately by stiff brush / roller / trowel in thin continuous film. Allow primer to dry.

Porous substrate may require two coats of primer. Second coat applied perpendicular to first dried coat.

### CLEANING

Immediately after application of **DANOFLOOR PRIMER EP**, use suitable aromatic solvent for cleaning application tools.

### PROPERTIES OF COMPONENTS

Property	Part A	Part B
Type	Resin	Hardener
Colour/Appearance	Yellowish Clear Liquid	Brownish Clear Liquid
% Solids at 120°C	>60	>80
Viscosity at 25°C	450 to 650 mPa.s	3000 to 6000 mPa.s

### APPLICATION DATA

Mix Ratio, PBW RESIN : HARDENER	100 : 50
Pot life at 25°C	1.5 to 2.0 hrs approx..
Theoretical Coverage per Coat*	6 to 8 m <sup>2</sup> /Kg. @80 to 100 micron d.f.t
Curing Time Touch Dry Recoating Time	6 to 8 Hours 12 to 16 Hours

\*Coverage is approximate and it depends upon the site conditions and surface porosity at the time of application.

## PROPERTIES OF APPLIED PRODUCT

Properties	Value	Standard
Mix Density at 25°C	1.11g/ml	IEC 455
Bond Strength	>1.5 mPa (Concrete Failure)	ASTM D4541

## PROPERTIES OF CURED MATERIAL

Specimens cured for 15 days at room temperature (25°C to 35°C).		
Properties	Standard	Value
Flexural strength	ISO 178	45 MPa
Impact strength	ISO 179	8.5 KJ/m <sup>2</sup>
Compressive strength	ISO 604	35 MPa
Tensile strength	ISO 527	25 MPa
Density at 25°C	IEC 455	1.11 g/ml (Typical)
Hardness, Shore D	ISO 868	75
Bond strength	ASTM D4541	35 Kg./cm <sup>2</sup> Concrete failure

## SUPPLY

**DANOFLOOR PRIMER EP** is supplied as two component comprising of Resin and Hardener. Resin Component is available in 5 Kg. pack size, Hardener Component is available in 2.5 Kg. pack size. It has a shelf life of 12 months when stored under the covered shed in sealed condition.

## PACKING

Available Packing	Resin	Hardener
Pack Size	5 Kg.	2.5 Kg.

## STORAGE

**DANOFLOOR PRIMER EP** must be stored above 5°C. Store under the shed & protect from extremes of temperature, heat, direct sunlight, spark and children.

## SAFETY PRECAUTIONS

As with all chemical products, care should be taken during use and storage of **DANOFLOOR PRIMER EP**.

**VERSION: R2, 201905**

**Disclaimer:** TIKI TAR DANOSA warrants that each of its products will be manufactured in accordance with the specifications in effect on the date of manufacture. While TIKI TAR DANOSA endeavors to ensure that information given herein is correct to the best of our knowledge, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it. We recommend that adequate tests be performed by you to determine if this product meet all of your requirements.

**Note:** Properties subject to change as per specific requirement. Field service where provided does not constitute supervisory responsibility. Suggestions made by TIKIDAN either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not TIKIDAN, are responsible for carrying out procedures appropriate to a specific application. TIKIDAN reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with the conditions and technical specifications in force at the date of order.

## TIKITAR DANOSA (INDIA) PRIVATE LIMITED

Tiki Tar Estate, Village Road, Bhandup (W), Mumbai - 400 078,  
Maharashtra, India. T: +91 22 4126 6699  
E: [info@tikidan.in](mailto:info@tikidan.in) | W: [www.tikidan.in](http://www.tikidan.in)

