

Polyester Scrim for Reinforcing Liquid Coatings

DESCRIPTION

ARMADURA I is a polyester scrim armor, designed to increase strength and durability of waterproofing and protective coatings, such as TIKIDAN REVESTIDAN, TIKIDAN TIKI AQUASEAL, TIKIDAN DANOCRET and other range of waterproofing and protective coatings.

ADVANTAGES

- Excellent tensile strength
- Crack resistant and good flexibility
- Imparts strength to liquid coatings enhancing its durability.

USES

ARMADURA I is use for

- Reinforcing and imparting additional strength to liquid applied waterproofing / protective coatings.
- Reinforcing layer in joints and cracks, as repair before applying the coating.

APPLICATION INSTRUCTIONS

- While first coat of liquid waterproofing / protective coating is still wet, spread required gsm of **ARMADURA I** as reinforcing layer on first coating layer and embed, while maintaining overlap of 5cm at seams.
- Cover **ARMADURA I** reinforcing layer with second application of liquid coating.
- Avoid wrinkling in **ARMADURA I** reinforcing layer while embedding between two applications of liquid coating.
- Do not unroll more than 2m in vertical application.
- Ensure that reinforcing fabric is cut to required size using sharp instrument, thus avoiding damage or tears in the product.

PACKING

ARMADURA I is supplied in roll form of standard size.

PROPERTIES OF THE PRODUCT

Properties	Units	ARMADURA IP 20	ARMADURA IP 34	ARMADURA IP 40	ARMADURA IC 40	Test Methods
Gsm	g/m ²	18 to 23	32 to 37	38 to 43	38 to 43	ERT 40.3--90
Thickness	mm	0.12 to 0.14	0.15 to 0.18	0.25 to 0.28	0.42 to 0.48	ERT 30.5--89
Tensile Strength, MD	N/5cm	40 to 50	65 to 75	90 to 100	150 to 165	ERT 20.2--89
Tensile Strength, CD	N/5cm	25 to 35	25 to 35	70 to 80	30 to 40	ERT 20.2--89
Elongation, MD	%	15 to 25	20 to 30	20 to 30	15 to 30	ERT 20.2--89
Elongation, CD	%	15 to 20	30 to 40	15 to 25	60 to 130	ERT 20.2--89
Tear Resistance, MD	N	3 to 8	----	8 to 12	----	----
Tear Resistance, CD	N	3 to 8	12-16	8 to 12	----	EDANA 70.4 - 99
Size	m	1.6m x 1000m	1.6m x 500m	1.6m x 500m	1.6m x 500m	----

MD - Machine Direction, CD - Cross Direction

VERSION: R1, 201812

Disclaimer: TIKI TAR DANOSA warrants that each of its products will be manufactured in accordance with the specifications in effect on the date of manufacture. While TIKI TAR DANOSA endeavors to ensure that information given herein is correct to the best of our knowledge, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it. We recommend that adequate tests be performed by you to determine if this product meet all of your requirements.

Note: Properties subject to change as per specific requirement. Field service where provided does not constitute supervisory responsibility. Suggestions made by TIKIDAN either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not TIKIDAN, are responsible for carrying out procedures appropriate to a specific application. TIKIDAN reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with the conditions and technical specifications in force at the date of order.

TIKITAR DANOSA (INDIA) PRIVATE LIMITED

Tiki Tar Estate, Village Road, Bhandup (W), Mumbai - 400 078,
Maharashtra, India. T: +91 22 4126 6699
E: info@tikidan.in | W: www.tikidan.in

