

# TIKIFLEX 3003

## Flexible Polyolefin Waterproofing Tape

### DESCRIPTION

**TIKIFLEX 3003** is a high performance waterproofing joint tape designed for water tightness of outside expansion and construction joints exposed to high and permanent water pressure.

**TIKIFLEX 3003** is highly elastic, root-resistant and chemically resistant tape and is suitable for installation with adhesives and sealants on various building substrates in critical areas with high and / or frequent movements.



### ADVANTAGES

- Ensures water tightness of structural connections.
- Easy to apply and user friendly.
- Fusible with standard hot air dryers.
- Long lasting elasticity and service life.
- Maintains elasticity even in low temperatures.
- Resistant to tear, wear and abrasion.
- Root resistant.
- Resistant to bacteria and the deformation of chemicals attacks.
- Resistant to ozone and U.V rays.
- Resistant to alkalis, acids and salt solutions (for special cases, test before using).

### USES

**TIKIFLEX 3003** is used for waterproof sealing of:

- Expansion and construction joints, including large ones and that subjected to considerable high and or frequent movements
- Dynamic cracks and natural joints on structures
- Corners and junctions before waterproofing treatment
- Pipes and drains
- Expansion joints in precast panels
- Expansion joints together with sealant application

For construction and maintenance works in:

- Above and below ground applications
- Tunnels and basements
- Road joints and hydraulic works
- Foundations and curtain walls
- Pools & Treatment plants
- Balconies and parapet joints
- Roofs and terraces
- Bridges and viaducts
- Dams, reservoirs and water ducts

### APPLICATION INSTRUCTIONS

#### SURFACE PREPARATION

All surfaces should be sound, clean, and dry, free from cracks, honeycombs, oil, grease, laitance and loose particles.

Newly laid cementitious systems should be at least 28 days old with moisture content <4%.

Irregularities on the substrate must be repaired.

TIKI POLYSEAL, polysulphide sealant application in the expansion joints is recommended prior to **TIKIFLEX 3003** application.

#### APPLICATION

Mix epoxy adhesive thoroughly, following the guidelines. Apply the well-mixed epoxy adhesive on both sides along the joint or crack on the prepared substrate, preferably with a notched trowel or spatula. Layer thickness should be about 1-2 mm. ensure that expansion joint is not covered with epoxy adhesive.

Immediately after application of epoxy adhesive, unroll and apply the **TIKIFLEX 3003** tape, pressing it against the adhesive, stretching the ends by hand, taking care to avoid wrinkling and air bubbles, until the underlying adhesive totally wets the sides of the **TIKIFLEX 3003** tape.

Apply second layer of epoxy adhesive on the sides of **TIKIFLEX 3003** tape, in order to protect it permanently from accidental damage and to obtain monolithicity of the end to the support.

For the joint between two adjacent **TIKIFLEX 3003** tape, grind the end edges with sandpaper and fuse the end laps (using a special hot air welding machine) overlapping about 10cm. For additional security of the overlapped seal, a small layer of epoxy adhesive should be applied on the welded flaps.

The final system resistances will be reached after about 7 days after laying, but already after 24 hours, 60-70% of the final performances can be obtained. In any case the performance after 24 hours will be much greater than those of a high quality concrete.

When sealing cracks, or narrow joints the **TIKIFLEX 3003** should not be fully bonded on the joint. Centre line of the tape must be kept clean for elongation, expansion and contraction

#### IMPORTANT POINTS

- Centre line of **TIKIFLEX 3003** must be kept clean for elongation.
- It is recommended to apply sealant (TIKI POLYSEAL) in expansion joints prior to **TIKIFLEX 3003** application.
- Liquid applied waterproofing coatings must be applied over epoxy adhesive for proper water-tightness.

#### FUSIBILITY

The product is fusible with standard hot-air-dryers (recommendation  $\geq 1500$  watt / 340°C). It is important to select a low temperature setting so that only the surface of the tape melts in order not to affect the tightness of the product. Parts to be welded must be roughened or sanded.

#### PROPERTIES

Property	Standard	Value
Colour	-----	Grey
Tear resistance – lengthwise	DIN EN 12311-2 Method B	$\geq 8$ N/mm <sup>2</sup>
Tear resistance – across	DIN EN 12311-2 Method B	$\geq 8$ N/mm <sup>2</sup>
Elongation at break – lengthwise	DIN EN 12311-2 Method B	$\geq 500$ %
Elongation at break – across	DIN EN 12311-2 Method B	$\geq 500$ %
Tear resistance (nail shank)- lengthwise	DIN EN 12310-1	$\geq 400$ N
Tear resistance (nail shank)- across	DIN EN 12310-1	$\geq 400$ N
Water vapour permeability	DIN EN 1931 Method B	$\geq 80$ m
Shore A hardness	-----	Approx. 87
Bonding strength	DIN EN 1348	$\geq 4$ N / mm <sup>2</sup> *
Peel test on wood carrier	-----	$\geq 100$ N *

Water tightness	DIN EN 1928-A 60 kPa/24 Std.	watertight
	DIN EN 1928-B 400 kPa/72 Std.	watertight
Burst pressure	-----	> 5 bar
UV-Resistance:	DIN EN ISO 4892-3	≥ 6500 h
Reaction to fire	DIN ISO 11925-2 EN 13501-1	Class E
Temperature Resistance	-30°C to 90°C	
Chemical Resistance	Resistance to Hydrochloric acid, Potassium hydroxide, Lactic Acid, Sulphuric acid, Sodium hypchlorite, Salt water and other chemicals	

\*Depends upon the type of adhesive used

## SUPPLY

**TIKIFLEX 3003** is supplied as pre-fabricated tape and is available in following dimensions and thickness:

Description	Value	Tolerance
Thickness	2 mm	± 0.1mm
Available widths	150,200,250,500 mm (widths between 100 mm & 1000 mm upon request)	± 2mm
Weight	1830 g / m <sup>2</sup>	± 100g/m <sup>2</sup>
Length per roll	20 Meter (Alternative make ups upon request)	± 1%

**Disclaimer:** TIKI TAR DANOSA warrants that each of its products will be manufactured in accordance with the specifications in effect on the date of manufacture. While TIKI TAR DANOSA endeavors to ensure that information given herein is correct to the best of our knowledge, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it. We recommend that adequate tests be performed by you to determine if this product meet all of your requirements.

**Note:** Properties subject to change as per specific requirement. Field service where provided does not constitute supervisory responsibility. Suggestions made by TIKIDAN either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not TIKIDAN, are responsible for carrying out procedures appropriate to a specific application. TIKIDAN reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with the conditions and technical specifications in force at the date of order

## TIKITAR DANOSA (INDIA) PRIVATE LIMITED

Tiki Tar Estate, Village Road, Bhandup (W), Mumbai - 400 078,  
Maharashtra, India. T: +91 22 4126 6699  
E: [info@tikidan.in](mailto:info@tikidan.in) | W: [www.tikidan.in](http://www.tikidan.in)



## STORAGE

**TIKIFLEX 3003** must be stored above 5°C. Store under the shed & protect from extremes of temperature, heat, direct sunlight. It has a shelf life of 12 months when stored under the covered shed in sealed condition. If packaging film has been opened, apply the material within 2 months.

## SAFETY PRECAUTIONS

As with all synthetic products, care should be taken during use and storage of **TIKIFLEX 3003**.