

DANOFLOOR UL EP



Epoxy Based Self Levelling Underlay Flooring System

DESCRIPTION

DANOFLOOR UL EP is solvent free epoxy based three component self-smoothing underlay and leveling screed, for use in conjunction with TIKIDAN range of epoxy and polyurethane floor coatings and floor topping systems.

ADVANTAGES

- Seamless application
- Good levelling and smoothing ability
- Excellent bonding to primed surface and epoxy/polyurethane overlay
- Exhibits good mechanical properties
- Environment friendly system
- Excellent abrasion resistance

USES

DANOFLOOR UL EP underlay and levelling screed system is used to seal undulations/profile imperfections on floor creating smooth and levelled surface before application of epoxy / polyurethane floor coatings and floor toppings in:

- Automobile and engineering industries
- Pharmaceutical, food, beverage and dairy industries
- Formulation and assembly units
- Workshops, garages and warehouses
- Convention centre, shopping mall and super market
- Trafficable areas and parking decks
- Chemicals and process industries

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

The surfaces must be sound, clean, dry, and free from cracks, undulations, oil, grease, laitance, loose particles.

New concrete surfaces should be minimum 28 days old and should be sound with tensile strength >1.5 mPa. The residual moisture content in the substrates should be <4%.

All joints in the substrate should be maintained while laying **DANOFLOOR UL EP** underlayer system.

SURFACE PRIMING

Apply **DANOFLOOR PRIMER EP** epoxy based primer @6 to 8 m²/Kg., on well prepared substrate covering the entire area uniformly. Allow the primer to dry. On very absorbent or porous surface, it is necessary to apply second coat of primer.

Refer TDS of **DANOFLOOR PRIMER EP** for technical and application details.

APPLICATION

DANOFLOOR UL EP is supplied as pre-weighed three components, ready to use at site.

The components of **DANOFLOOR UL EP** shall be mixed by taking **DANOFLOOR UL EP Resin** component in a clean container followed by addition and gradual mixing of **DANOFLOOR UL EP Hardener** component using slow speed heavy duty electric stirrer to achieve homogeneous mix. Finally, **DANOFLOOR UL EP Filler** component is added gradually under continuous stirring until homogeneous mix is obtained.

The prepared mix of **DANOFLOOR UL EP** is spread using serrated toothed trowel to desired thickness (1mm to 3mm). Immediately roll the spread material using spike roller to remove air entrapment and avoid pinholes formation. Allow the applied system to cure for 24 hours before application of overlay.

APPLICATION DATA

Mix Ratio PBW Resin: Hardener: Filler (For 1mm thickness)	100 : 100 : 150
Mix Ratio PBW Resin: Hardener: Filler (For 2 to 4mm thickness)	100 : 100 : 350
Pot life at 30°C	≈ 45 Minutes
Curing Schedule Foot traffic / Light load Full traffic load	24 to 48 Hours 7 Days
*Total Mix Required to Cover 10m ² Area @1mm @ 2mm @ 3mm	18 Kg. to 19 Kg. 36 Kg. to 40 Kg. 52 Kg. to 60 Kg.

*Coverage / Consumption is approximate and it depends upon the site conditions and surface porosity at the time of application.

PROPERTIES OF APPLIED PRODUCT

Properties	Values	Test Standard
Compressive Strength	>60N/mm ²	ISO 604
Flexural Strength	>45 N/mm ²	ISO 178
Tensile Strength	>22 N/mm ²	ISO 527
Bond Strength	>3N/mm ² (Concrete Failure)	ASTM D4541
Impact Resistance	>8 Joules	ASTM D2794

*Properties tested under laboratory condition for specimens cured for 15days @30°C. Properties may vary based on actual site conditions.

CLEANING

Immediately after application of **DANOFLOOR UL EP**, use suitable solvent for cleaning application tools.

SUPPLY

DANOFLOOR UL EP is supplied as a three component comprising of Resin, Hardener and Filler. Resin Component is available in 25Kg. and 10 Kg. pack size, Hardener Component is available in 25 Kg. and 10 Kg. pack size and Filler Component is available in 10 Kg. pack size. It has a shelf life of 12 months when stored under the covered shed in sealed condition.

Available Packing	Resin	Hardener	Filler
Pack Size	25 Kg. and 10 Kg.	25 Kg. and 10 Kg.	10 Kg

STORAGE

DANOFLOOR UL EP must be stored above 5°C. Store under the shed & protect from extremes of temperature, heat, direct sunlight, and children.

SAFETY PRECAUTIONS

As with all chemical products, care should be taken during use and storage of **DANOFLOOR UL EP**.

VERSION R2:201901

Disclaimer: TIKI TAR DANOSA warrants that each of its products will be manufactured in accordance with the specifications in effect on the date of manufacture. While TIKI TAR DANOSA endeavors to ensure that information given herein is correct to the best of our knowledge, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it. We recommend that adequate tests be performed by you to determine if this product meet all of your requirements.

Note: Properties subject to change as per specific requirement. Field service where provided does not constitute supervisory responsibility. Suggestions made by TIKIDAN either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not TIKIDAN, are responsible for carrying out procedures appropriate to a specific application. TIKIDAN reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with the conditions and technical specifications in force at the date of order.

TIKITAR DANOSA (INDIA) PRIVATE LIMITED

Tiki Tar Estate, Village Road, Bhandup (W), Mumbai - 400 078,
Maharashtra, India. T: +91 22 4126 6699
E: info@tikidan.in | W: www.tikidan.in