

TIKIDAN PIPE WRAP 7L



Pipe Wrapping Tape

DESCRIPTION

TIKIDAN PIPE WRAP 7L is anti-corrosive impermeable non-metallic machine compacted 7 layer engineered advanced polymeric composite tape. Consisting of two inner cores. One of the core is armour of fibreglass mat, which imparts the tape toughness, dimensional stability and mechanical strength and the other core is Polyester mat imparting good mechanical strength thereby providing extra protection to pipe wrap against soil stresses and impact damage during handling and installation.

TIKIDAN PIPE WRAP 7L complies to IS: 10221:1982, Appendix "B".

USES

TIKIDAN PIPE WRAP 7L is used for protection of underground and non-exposed metallic pipelines from detrimental effects of corrosion and such areas Include:

- Water supply pipelines
- Fire hydrant supply pipelines
- Coal log supply pipelines
- Chemical supply pipelines
- Sewage pipelines
- Waste water disposal pipelines
- Coarse particles (ores and minerals) conveying pipelines
- Mineral waste transport and disposal pipelines
- Electric supply cables carrying pipelines
- Telecommunication cables carrying pipelines

ADVANTAGES

- Outstanding Pipe Protection
- Excellent Conformability to Pipe Sections
- Excellent Adhesion to Self and Primed Metal
- Quick Turnaround
- Consistent Quality

- Uniform and Durable Performance
- Trouble Free Application with High Speed Wrapping Machine
- Stands Up to Stress
- Stays Intact
- Withstands Repeated Handling at the Plant and at Site
- Performs in Wide Temperature Range
- Resistance to Cathodic Disbonding
- Excellent Resistance to Chemicals

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

The external surface of pipe shall be thoroughly cleaned to remove rust, dirt, dust, moisture, grease, oil, mill scale, welding splatter, slivers, scabs, foreign substances etc., using appropriate tools & methods. Presence of moisture on pipe, if any shall be removed by warming the pipe surface using gas torch.

SURFACE PRIMING

On prepared surface, apply a coat of quick drying anti-corrosive synthetic primer TIKI PRIME (SY) compatible with **TIKIDAN PIPE WRAP 7L** @ 8m² to 10 m² per litre (approx.) uniformly covering and wetting the pipe surface to promote adhesion of **TIKIDAN PIPE WRAP 7L**.

APPLICATION

As soon as the prime coat is dry, **TIKIDAN PIPE WRAP 7L** is installed using Torch-On Method. Depending upon the diameter of pipe, **TIKIDAN PIPE WRAP 7L** is wrapped around the pipe in spiral / cigarette method and bonded completely to the primed surface by thermos fusion hot process. Cut **TIKIDAN PIPE WRAP 7L** rolls to required size and mark proper overlaps (>12mm). Leave pipes untreated 150mm to 200mm from ends on either side to facilitate welding.

Maintaining the alignment of pipe wrap, its underside should be warmed using gas torch to soften the coating compound.

When underside heating of pipe wrap shows shiny coating surface, it should be roll forwarded and wrapped under sufficient tension to ensure good adhesion. The pipe wrap should be pressed firmly from above against the pipe surface to obtain superior and permanent bonding ensuring intimate contact with the primed pipe thereby preventing air pockets / holidays beneath the applied pipe wrap.

PROPERTIES OF TAPE

Properties	Values
Softening point of the component	65°C to 121°C
Penetration (25°C, 100gm, 5sec.)	3 dmm to 20 dmm
Filler	20% to 30%
Longitudinal Tensile Strength	>650 N/5cm
Transversal Tensile Strength	>450 N/5cm
Elongation Longitudinal	>40%
Elongation Transversal	>35%
Heat Resistance (Does not drip)	>100°C

TIKIDAN PIPE WRAP 7L complies to IS: 10221:1982, Appendix "B".

PROPERTIES OF PRIMER

Properties	Values
Volatile matter	75 % max
Viscosity by B4 flow cup standard viscometer @ 20°C	35 to 60 seconds
Drying time	5 to 15 minutes
Flash point, Pensky martin closed cup	23°C min.

SUPPLY

The **TIKIDAN PIPE WRAP 7L** is supplied in roll size of 1m x 10m in 3mm/4mm thickness.

PROTECTION

In order to prevent damage from U.V. light, the pipes coated with **TIKIDAN PIPE WRAP 7L** should not be left open exposed to Sun light for more than 5 days. In the event of exposure for more than 5 days, it should be protected by, temporary coverings, such as craft paper, white wash etc. This prevents excessive heating of the pipe wrap surface arising out of absorption of solar radiation and its U.V. degradation.

SAFETY PRECAUTIONS

As with all sheet products, care should be taken during use and storage of **TIKIDAN PIPE WRAP 7L**.

VERSION: R2, 201912

Disclaimer: The technical information, and, in particular, the recommendations relating to the application and end-use of Tiki Tar Danosa (TIKIDAN) products, are given in good faith based on TIKIDAN's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with TIKIDAN's recommendations. The information herein is of a general nature and no assumption can be made as to a product's suitability for a particular use or application and no warranty in respect of merchantability or of fitness for a particular purpose can be inferred from this information. The user alone is fully responsible for the product's suitability for the intended application and purpose. TIKIDAN reserves the right to change the properties of its products.

Note: Field service where provided does not constitute supervisory responsibility. Suggestions made by TIKIDAN either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not TIKIDAN, are responsible for carrying out procedures appropriate to a specific application. TIKIDAN reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with the conditions and technical specifications in force at the date of order. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

TIKITAR DANOSA (INDIA) PRIVATE LIMITED

Tiki Tar Estate, Village Road, Bhandup (W), Mumbai - 400 078, Maharashtra, India. T: +91 22 4126 6699
E: info@tikidan.in | W: www.tikidan.in



ISO 9001:2015