

TIKI AQUASEAL AR



Acrylic-PU Based Crack Bridging and Waterproofing Protective Coating

DESCRIPTION

TIKI AQUASEAL AR is single component ready to use white colored Acrylic-Polyurethane Resin dispersion based U.V resistant elastomeric membrane coating for protection of all R.C.C structures.

ADVANTAGES

- Seamless
- Good adhesion to primed surface
- White colour – heat reflective finish providing moderate insulation from solar heat
- UV and weather resistant
- Good resistant to carbonation and chloride attack
- Elastomeric - high crack bridging ability
- Good resistance to water, salts, sea water, mild acids and alkalis and saline atmosphere
- Solvent free - V.O.C compliant
- Good resistance against algae and fungi.
- Dirt pick-up resistant and good cleanability
- Breathable-allows for escape of entrapped moisture/ water vapour through the treatment.
- Waterproofing protection coat

USES

TIKI AQUASEAL AR is suitable for application on:

- Roof slabs, terraces, balconies, parapet walls etc.
- Old and new surfaces, vertical as well as horizontal
- Structures with complex geometry like domes, arches, silos, chimneys, corrugated sheets etc.
- Structures exposed to marine / saline atmosphere

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

The surfaces must be sound, clean, dry, and free from cracks, honeycombs and undulations, laitance, oil, grease, traces of paints and loose particles.

New concrete should be 28 days old with moisture content less than 4%. All existing cracks and expansion joints shall be treated with **TIKISEAL PU25 / TIKISEAL PU40** polyurethane sealant.

REINFORCING CORNERS & JUNCTIONS

All corners, inside and outside including junctions, should be reinforced using 0.63 mm thick and 120mm wide thermoplastic elastomer coated alkali resistant waterproofing tape **TIKIFLEX 1001**, the tape sandwiched between two coats of **TIKI AQUASEAL AR**.

The tape should be embedded in first wet coat while maintaining overlap of 5cm. Second coat is applied perpendicular to dried first coat fully covering the reinforcing tape

SURFACE PRIMING

Apply **TIKI AQUASEAL AR** diluted with water in 2:1 ratio as primer @6 to 8 m²/Kg., (coverage may vary depending upon the nature and texture of the substrate), on well-prepared substrate covering the entire area uniformly. Allow the primer to dry.

On very absorbent or porous surface, it is necessary to apply second coat of primer.

APPLICATION

TIKI AQUASEAL AR is applied in two coats by brush or roller or airless spray @ 6 to 8 m²/Kg./coat.

While first coat is still wet, depending upon the project requirement, it is recommended to embed reinforcing layer of 50 gsm non-woven polyester scrim in first wet coat while maintaining overlap of 5cm.

Second coat is applied perpendicular to dried first coat fully covering the reinforcing layer.

PROPERTIES

PROPERTIES	VALUE
Type	Acrylic-PU Dispersion
Colour**	White
Full Cure	7 days
Coverage in 2 Coats*	3 to 4 m ² / Kg.

*Coverage / Consumption is approximate and it depends upon the site conditions and surface porosity at the time of application.

**For other colours, Universal stainers can be used after confirming the compatibility with the coating.

TIKI AQUASEAL AR coating can bridge cracks up to 0.2mm width. The crack bridging ability can be enhanced with additional coats of the system.

CLEANING

Immediately after application of **TIKI AQUASEAL AR**, use water for cleaning application tools.

SUPPLY

TIKI AQUASEAL AR is supplied in 25 Kg., and 50 Kg., pack size.

STORAGE

TIKI AQUASEAL AR must be stored above 5°C. Store under the shed & protect from extremes of temperature, heat, direct sunlight. The shelf life is 6 months in sealed container.

SAFETY PRECAUTIONS

As with all chemical products, care should be taken during use and storage. **TIKI AQUASEAL AR** is non-toxic and non-flammable. Avoid contact with skin, eyes, mouth and food. For further detail, refer to Material Safety Data Sheet.

VERSION: R2, 202004

Disclaimer: The technical information, and, in particular, the recommendations relating to the application and end-use of Tiki Tar Danosa (TIKIDAN) products, are given in good faith based on TIKIDAN's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with TIKIDAN's recommendations. The information herein is of a general nature and no assumption can be made as to a product's suitability for a particular use or application and no warranty in respect of merchantability or of fitness for a particular purpose can be inferred from this information. The user alone is fully responsible for the product's suitability for the intended application and purpose. TIKIDAN reserves the right to change the properties of its products.

Note: Field service where provided does not constitute supervisory responsibility. Suggestions made by TIKIDAN either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not TIKIDAN, are responsible for carrying out procedures appropriate to a specific application. TIKIDAN reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with the conditions and technical specifications in force at the date of order. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

TIKITAR DANOSA (INDIA) PRIVATE LIMITED

Tiki Tar Estate, Village Road, Bhandup (W), Mumbai - 400 078,
 Maharashtra, India. T: +91 22 4126 6699
 E: info@tikidan.in | W: www.tikidan.in

