

DANOFLOOR PRIMER EPW



Epoxy Based Primer

DESCRIPTION

DANOFLOOR PRIMER EPW is specially formulated two component aqueous epoxy based primer suitable for application on various substrates for promoting adhesion of Epoxy / Polyurethane floor and wall coatings and floor topping systems.

ADVANTAGES

- Low exothermic in nature
- Extended workability and pot life
- Bonds strongly with the concrete, masonry, epoxy and polyurethane screeds, top coats and other substrates
- Non-blushing in humid and low temperature environments
- Less viscous—deep penetration in to substrate pores
- V.O.C free

USES

DANOFLOOR PRIMER EPW is used

- To promote the adhesion of TIKIDAN epoxy and polyurethane range of floor toppings, coatings and repair mortars with various substrates including cementitious, metals, epoxies & polyurethane.
- To seal substrate pores and bind loose particles on substrates enhancing the adhesion of subsequent coatings/toppings.
- As primer / sealer coat over the TIKIDAN epoxy and polyurethane cementitious underlays, before application of polymeric overlays.
- In areas where use of solvent based primers are not permitted.
- As adhesive for bonding thin cementitious renders to old surfaces.

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

All surfaces should be sound, clean, and dry, free from cracks, honeycombs, oil, grease, laitance and loose particles.

Newly laid cementitious systems should be at least 28 days old. Residual moisture content in surface should be <4% before applying **DANOFLOOR PRIMER EPW**.

APPLICATION

Gradually mix **DANOFLOOR PRIMER EPW Resin** and **DANOFLOOR PRIMER EPW Hardener** component for 3 to 5 minutes until it becomes homogeneous. Apply mixed component immediately by stiff brush / roller / trowel in thin continuous film. Allow the primer to dry.

Porous substrate may require two coats of primer. The second coat of primer is applied perpendicular to first dry coat.

CLEANING

Immediately after application of **DANOFLOOR PRIMER EPW**, use water for cleaning application tools.

APPLICATION DATA

Mix Ratio PWB (Resin : Hardener)	100 : 200
Pot life at 25°C	≈ 45 Minutes
Coverage per Coat*	3 to 5 m ² /Kg., @ 50 to 70 micron d.f.t
Curing Schedule	
Touch Dry	2 to 3 Hours
Recoating Time	8 to 12 Hours
Hard Dry	12 to 16 Hours

*Coverage is approximate and it depends upon the site conditions and surface porosity at the time of application.

PROPERTIES OF COMPONENTS

Property	Resin	Hardener
Colour/Appearance	Milky White Liquid	Brownish Clear Liquid
% Solids at 105°C	>55	>15
Viscosity at 25°C	20 to 60 (B4 Cup)	10 to 15 (B4 Cup)

SUPPLY

DANOFLOOR PRIMER EPW is supplied in 7.5 Kg. pack. It has a shelf life of 12 months when stored under the covered shed in sealed condition.

Packing: 7.5 Kg.

Resin	Hardener
2.5 Kg.	5 Kg.

STORAGE

DANOFLOOR PRIMER EPW must be stored above 5°C. Store under the shed & protect from extremes of temperature, heat, direct sunlight, and children.

SAFETY PRECAUTIONS

As with all chemical products, care should be taken during use and storage of **DANOFLOOR PRIMER EPW**.

VERSION: R4, 202007

Disclaimer: The technical information, and, in particular, the recommendations relating to the application and end-use of Tiki Tar Danosa (TIKIDAN) products, are given in good faith based on TIKIDAN's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with TIKIDAN's recommendations. The information herein is of a general nature and no assumption can be made as to a product's suitability for a particular use or application and no warranty in respect of merchantability or of fitness for a particular purpose can be inferred from this information. The user alone is fully responsible for the product's suitability for the intended application and purpose. TIKIDAN reserves the right to change the properties of its products.

Note: Field service where provided does not constitute supervisory responsibility. Suggestions made by TIKIDAN either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not TIKIDAN, are responsible for carrying out procedures appropriate to a specific application. TIKIDAN reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with the conditions and technical specifications in force at the date of order. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

TIKITAR DANOSA (INDIA) PRIVATE LIMITED

Tiki Tar Estate, Village Road, Bhandup (W), Mumbai - 400 078,
 Maharashtra, India. T: +91 22 4126 6699
 E: info@tikidan.in | W: www.tikidan.in

