

Acrylic Polymer Modifier for Cementitious Systems

DESCRIPTION

DANOCRET AR-HS is acrylic polymer-based polymer modifier for use with cementitious compositions as waterproofing slurry coating, water resistant bonding agent, protective coating.

USES

As polymer modifier in conjunction with cementitious composition, **DANOCRET AR-HS** is used for:

- Waterproofing basement and retaining wall, lift pits, toilets and bathrooms, wet areas, water tanks, swimming pools, terraces, and other areas demanding watertight treatment.
- Bonding new cementitious surfaces with old cementitious surfaces in repair works.
- Preparations of polymer modified cementitious protective coating.

ADVANTAGES

Cementitious compositions made with **DANOCRET AR-HS** is characterised by:

- Increased resistance to water ingress and cracking.
- Enhanced adhesion with substrates.
- Increased water tightness.
- Good flexibility and crack bridging ability.
- Breathable – allows entrapped moisture to escape.
- High resistance to corrosive atmosphere.
- Improved workability.
- Lower water-cement ratio.

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

The surface to be treated must be clean and sound free of loose dust, laitance, foreign particles, curing compound, mould release agent & other contaminants that may compromise adhesion of treatment adversely.

Spalled concrete or honeycombed surface should be repaired using polymer modified cementitious repair mortar modified with **DANOCRET I-LATEX**.

Cracks should be cut to V-shape and filled using cementitious mortar modified with **DANOCRET I-LATEX**.

Never use **DANOCRET AR-HS** modified waterproofing slurry directly on unsound surface, brick coba or lime mortar.

PROPERTIES of DANOCRET AR-HS

Properties	Values
Appearance	Milky white pourable emulsion
Emulsifying System	Synthetic anionic
Total Solids (%)	57 ± 1.0
pH at 25°C	8.0 ± 0.5
Brookfield Viscosity RVT (CPS) SP.3, 20 RPM at 25°C	2500 Max.
Density (gm/cm ³)	1.015 ± 0.015
Compatibility	Compatible with all grades of cement

POLYMER MODIFIED CEMENTITIOUS WATERPROOFING MIX PREPARATION

2 parts of Cement by weight is gradually added to 1 part of **DANOCRET AR-HS** by weight in a separate container under continuous stirring until homogeneous lump free creamy consistency mix is obtained. Allow the prepared mix to stand for 5 minutes before using. The prepared mix should be used within 30 minutes after mixing.

APPLICATION

Prior to application of waterproofing slurry, damp the surface to be coated by sprinkling water. Apply slurry uniformly by brush in two coats, the second coat shall be applied perpendicularly on dried first coat within 24 hours of application of first coat.

If application of protective render coat is required, then quartz sand is sprinkled on the wet second coat for forming mechanical key for subsequent protection coat.

COVERAGE

Waterproofing slurry coat consisting of mixture of 1 Kg. of **DANOCRET AR-HS** with 2 Kg. of cement covers 1.4 to 1.6 m² area @ 1mm thickness in 2 coats.

PROPERTIES of WATERPROOFING SLURRY

Properties*	Values
Mix Ratio Cement: DANOCRET AR-HS	2:1 by Weight
Mix Density	1800 to 2000 Kg. /m ³
Pot Life	40 minutes @ 30°C 20 minutes @ 40°C
Re-Coatability	6 to 24 hours

*Properties are indicative, tested under ideal laboratory condition. Properties Varies depending on site conditions and mix constituents.

BOND COAT

DANOCRET AR-HS with minimum solid content of ≥55% by weight can be suitably used as bonding slurry coat to promote the adhesion of cementitious treatments with cementitious substrate. **DANOCRET AR-HS** should be mixed with cement in 1:1 ratio by weight and applied @ 4 to 6 m²/ Kg., as bond coat, to produce minimum pull-off bond strength of >1MPa.

CURING

The final layer of applied polymer modified cementitious systems shall be allowed to initially cure for at least 3 days by spraying water and thereafter shall be allowed to dry out for air curing.

SUPPLY

DANOCRET AR-HS is supplied in 26Kg., and 220Kg. pack sizes.

STORAGE

DANOCRET AR-HS must be stored above 5°C. Store under the shed & protect from extremes of temperature, heat, direct sunlight. The shelf life is 12 months in sealed unopened container.

SAFETY PRECAUTIONS

As with all chemical products, care should be taken during use and storage of **DANOCRET AR-HS**. Use gloves, goggles and barrier cream. Avoid contact with skin. Ensure adequate ventilation during application. For further detail, refer to Material Safety Data Sheet.

VERSION: R4, 202203

Disclaimer: The technical information, and, in particular, the recommendations relating to the application and end-use of Tiki Tar Danosa (TIKIDAN) products, are given in good faith based on TIKIDAN's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with TIKIDAN's recommendations. The information herein is of a general nature and no assumption can be made as to a product's suitability for a particular use or application and no warranty in respect of merchantability or of fitness for a particular purpose can be inferred from this information. The user alone is fully responsible for the product's suitability for the intended application and purpose. TIKIDAN reserves the right to change the properties of its products.

Note: Field service where provided does not constitute supervisory responsibility. Suggestions made by TIKIDAN either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not TIKIDAN, are responsible for carrying out procedures appropriate to a specific application. TIKIDAN reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with the conditions and technical specifications in force at the date of order. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

TIKITAR DANOSA (INDIA) PRIVATE LIMITED

Tiki Tar Estate, Village Road, Bhandup (W), Mumbai - 400 078,
Maharashtra, India. T: +91 22 4126 6699
E: info@tikidan.in | W: www.tikidan.in

