

CONFORDAN

Flexible cross-linked polyethylene membrane, finished in an aluminized LPDE film.

It is used as an acoustic insulation and protection against humidity under laminated floors.



TECHNICAL DATA

TECHNICAL DATA	VALUE	UNIT	STANDARD
Thickness	3	mm	EN 1923
Thickness tolerance	< 10	%	EN 823
Length and width tolerance	< 10	%	EN 822
Reduction of transmitted impact noise, ΔL_n	18	dB	EN 140-8 EN 717-2
Dynamic stiffness	≤ 100	MN/m ³	EN 29052-1
Density	$40 \pm 10\%$	kg/m ³	EN 845
Hysteresis load	> 1.9	Nm	EN 3386-1
Water absorption under hydrostatic pressure			
Water diffusion factor, μ	> 2000	-	EN-12086
Compression strength to 25%	50	kPa	UNE EN ISO 3386-1
Compression set 24 h, 50% comp., 23°C	< 10	%	EN 1856
Tensile strength	> 240	kPa	EN 1798
Reaction to fire	F	Euroclase	EN 13501-1
Thermal conductivity	0.040	w/mK	EN 12667 EN 12939

STANDARDS AND CERTIFICATION

Acoustic certifications resulting from approved laboratory tests.

Laboratory	Test (EN 140-3) No	Result (EN 717-2) ΔL_n
DANOSA (CONFORDAN)	DAN-009-TAR01	18 dB

SCOPE

- Anti-dampness and separation underlay for the laminate flooring.
- Acoustic insulation against impact noise in supports of over 500 Kg/m² for residential buildings, hotels, hospitals, etc.
- Floor renewals for residential buildings

PRESENTATION

PRESENTATION	VALUE	UNIT
Length	25	m
Width	0.95	m
Total thickness	3	mm
Product Code	620033	-

INSTRUCTION FOR USE

An installation of the Confordan is shown in the following pictures:



1. Extend and seal
2. Place 1st board
3. Set as system flooring
4. Aluminum tape to take away static electricity

INDICATIONS AND IMPORTANT RECOMMENDATIONS

- Differences in height of or above 3 mm in 1 m must be previously leveled with leveling paste.
- The panels must stay at least 48h acclimatizing to the room where they will be installed at a temperature of at least 18 °C, the relative humidity between 40% and 70%.
- Scotia must have a thickness of at least 15 mm to cover up the expansion gap and it must leave a small separation sealed with a silicone cord.
- Sealing tapes of natural aluminum must be used in order to reduce the static electricity.
- Check the product's technical sheet on safety.
- For further information, please contact our technical staff.

WARNING

The information that appears in the following document makes reference to the uses and utilities of danosa's products and systems, and it is based on the knowledge that have been learnt until present, by danosa. This is only possible if products have been stored and used in an appropriate way. Nevertheless, danosa is not responsible for unsuitable uses of the products neither any other facts, such as meteorological facts. So danosa is just responsible for the quality related to the provided products. danosa reserves the right to carry out modifications without previous notice. The values that appear in the technical sheet are the results of the tests that have been performed in our laboratory. September 2006 Web site: www.danosa.com E-mail: export@danosa.com Phone number: +34 949 888 210